

AMENDMENTS TO THE CLAIMS

This listing of claims replaces all prior versions of claims in the application.

1. (Currently amended): A polarizing film comprising:
a long polymer film having an MD direction and a TD direction; and
a dichroic substance,
wherein the polarizing film has an absorption axis in the TD direction of the polarizing
film [[.]] , and
wherein the length in the MD direction of the polarizing film is not smaller than five
times as long as the length in the TD direction of the polarizing film.

2. (Cancelled).

3. (Original): The polarizing film according to claim 1,
wherein the polarizing film is produced by stretching the long polymer film in the TD
direction.

4. (Currently amended): The polarizing film according to claim 1,
wherein the polarizing film is produced by:
stretching the long polymer film in the TD direction with the stretching ratio of 1.1 to
20 times as long as the initial width; and

shrinking the long polymer film in the MD direction with the shrinking ratio of 70 to 99% as long as the initial length.

5. (Original): The polarizing film according to claim 1,
wherein the polarizing film is produced by dyeing the long polymer, which is stretched in the TD direction, with a iodine by using an aqueous solution containing the iodine.

6. (Original): The polarizing film according to claim 1,
wherein the polarizing film is produced by dyeing the long polymer, which is stretched in the TD direction and shrunk in the MD direction, with a iodine by using an aqueous solution containing the iodine.

7. (Original): The polarizing film according to claim 5,
wherein the polarizing film is produced by dyeing the long polymer film with the iodine by applying the aqueous solution containing the iodine onto the long polymer film.

8. (Original): A laminated film comprising:
a polarizing film according to claim 1; and
a retardation film having a slow axis in the MD direction, which comprises a long polymer film,

wherein the MD direction of the polarizing film corresponds to the MD direction of the retardation film.

9. (Original): The laminated film according to claim 8,
wherein the retardation film comprises a uniaxially stretched film.

10. (Original): The laminated film according to claim 8,
wherein the retardation film comprises an optically uniaxial layer comprising a liquid
crystal material.

11. (Original): The laminated film according to claim 8,
wherein the retardation film comprises a birefringent layer comprising a non-liquid
crystal material having a birefringence of not lower than 0.005.

12. (Original): The laminated film according to claim 8,
wherein the retardation film is a composite film comprising a birefringent layer
provided on a birefringent polymer film.

13. (Original): The laminated film according to claim 11 or 12,

wherein the birefringent layer comprises a solid polymer containing at least one selected from: polyetherketone; polyamide; polyester; polyimide; polyamideimide; and polyesterimide.

14. (Original): The laminated film according to claim 13,
wherein the birefringent layer is a solid polymer comprising polyimide.

15. (Original): The laminated film according to claim 11 or 12,
wherein the birefringent layer has a relationship
 $n_x > n_y > n_z$,
wherein n_x is the maximum in-plane refractive index, n_y is an in-plane refractive index in a direction perpendicular to the direction of n_x , and n_z is a thicknesswise refractive index.

16. (Original): A liquid crystal display comprising a polarizing film according to claim 1 that is disposed outside of a liquid crystal cell.

17. (Original): A liquid crystal display comprising a laminated film according to claim 8 that is disposed outside of a liquid crystal cell.

18. (Withdrawn): A process for producing a polarizing film comprising:
unrolling a polymer film successively;

stretching the polymer film in the TD direction; and
dyeing the stretched film.

19. (Withdrawn): The process for producing a polarizing film according to claim 18;
wherein the stretching in the TD direction is carried out by a tenter stretching
machine.